

Product data sheet



Product: 5011AG
MIRO-SILVER® 5
Reflector Diffuse

4700/0403/001/08.13

Alloy ¹ Al 99,7
Hardness ² hard

Treatment front side (S1) brightened, anodised and PVD-coated
Treatment reverse side (S2) anodised

Coating system (S1) PVD - based on AG 99,95

Iridescence assessment (S1) absolutely free of interference colours

Supply form

Coil, strip, sheet, blanks
Thickness [inch] 0.0118 - 0.0197
Width up to [inch] 49.2126

Optical Values

Total light reflection	[%]	≥ 97	DIN 5036-3 (U-Globe) (8°)
Diffuse light reflection	[%]	82 - 92	DIN 5036-3 (U-Globe) (8°)
Brightness 60° along	[-]	65 - 80	ISO 7668 (60°)
Brightness 60° across	[-]	25 - 50	ISO 7668 (60°)
Reflectance class		A+	DIN EN 16268

Mechanical Properties

Yield strength Rp 0,2	[ksi]	21.8 - 25.4
Tensile strength Rm	[ksi]	23.2 - 26.8
Elongation at break A50	[%]	≥ 2
Bending radius		≥ 1.5 x gauge of material

Tolerances

Thickness	[inch]	0.0118 - 0.0197 ± 0.0016
Width/Coil	[inch]	+ 0.1181 / - 0.0000
Width Slit Coil	[inch]	± 0.0079 standard
Longitudinal Curvature	[inch]	≤ 0.0394 on a measuring length of 39.3700
Length	[inch]	0.0000 - 23.6220 + 0.0394 / - 0.0000
	[inch]	23.6221 - 59.0551 + 0.0591 / - 0.0000
	[inch]	59.0552 - 98.4252 + 0.0984 / - 0.0000
	[inch]	98.4253 - 137.7953 + 0.1378 / - 0.0000
Flatness	[%]	1 % of wavelength, max. 0.3150 [inch]
Transversal Divergency	[inch]	≤ 0.0591 (D1-D2) other tolerances on request

Protective Film

Protective Film Type	[-]	PE - Film
Protective Film Thickness	[µm]	50 - 60

¹ based on DIN EN 573-3 (Aluminium) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium) resp. Rolling mill standard



Product data sheet



4700/0403/001/08.13

¹ based on DIN EN 573-3 (Aluminium) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium) resp. Rolling mill standard

05/17/2022 13:31:56 Valid only on print date

